



	Natural	Buna S	Neoprene	Buna N	Butyl	Hypalon	Silicon	Viton	Teflon
Acetaldehyde	F	P	P	P	G	-	-	P	G
Acetamide	F	F	F	G	F	-	-	-	-
Acetic Acid, Crude	X	X	F	F	F	F	-	X	G
Acetic Acid, Dilute	F	X	P	F	F	X	G	X	G
Acetic Acid, Glacial									
Acetic Anhydride	-	X	P	P	G	G	-	X	G
Acetone	F	G	X	P	G	F	G	X	G
Air (150 F)	G	G	G	G	G	G	-	-	-
Aluminum Chloride (150F)	G	G	G	G	G	G	-	G	G
Aluminum Fluoride (150F)	G	G	G	G	G	G	-	-	-
Aluminum Sulfate (150F)	G	G	G	GG	G	G	-	-	G
Alums (150F)	G	G	G	G	G	G	-	-	G
Ammonia Gas, Cold	G	G	G	G	G	-	-	-	-
Ammonium Gas, Hot (150F)	X	X	G	X	X	-	-	-	-
Ammonium Carbonite	G	G	P	P	G	-	-	-	-
Ammonium Chloride	G	G	G	G	G	-	-	-	G
Ammonium Hydroxide	X	X	G	X	X	G	G	G	G
Ammonium Nitrate	G	G	G	G	G	G	-	G	G
Ammonium Nitrite	X	X	G	X	-	-	-	-	-
Ammonium Persulfate	-	-	P	-	-	-	-	-	-
Ammonium Phosphate	G	G	G	G	G	-	-	-	-
Ammonium Sulfate	G	G	G	G	G	G	G	-	G
Ammonium Sulfide	-	-	P	-	-	-	-	-	-
Amyl Acetate	F	P	P	P	-	P	-	X	G
Amyl Alcohol	G	G	G	G	G	G	-	-	-
Aniline	P	P	P	P	G	F	-	-	-
Aniline Dyes	F	F	F	F	G	F	-	-	-
Asphalt	P	P	F	F	P	F	G	G	G
Barium Chloride (150F)	G	G	G	G	G	G	G	-	-
Barium Hydroxide (150F)	G	G	G	G	G	G	G	G	G
Barium Sulfide (150F)	G	G	P	GG	G	G	-	G	G
Beer	G	G	G	P	G	G	-	G	G
Beet Sugar Liquors	G	G	G	G	G	G	-	G	G
Benzaldehyde	X	P	P	P	G	-	G	X	G
Benzene, Benzol	P	P	P	P	P	P	P	G	-
Benzine, Petroleum, Ether, Naptha	P	P	P	P	P	F	P	G	-
Benzol	P	P	P	P	P	X	P	-	-
Benzyl Alcohol	G	F	G	P	P	-	-	-	-
Benzyl Chloride	X	X	P	P	G	-	-	-	-
Black Sulfate Liquors	G	G	G	G	G	G	-	-	G
Blast Furnace Gas	X	X	X	X	X	X	-	-	-
Borax	G	G	X	F	G	G	G	F	G
Boric Acid	G	G	G	G	G	G	G	G	G
Bromine	P	P	F	X	P	G	-	G	G
Butane	P	P	F	X	P	G	-	G	G
Butter	P	P	G	G	-	-	-	-	-
Butyl Acetate	F	P	P	P	F	F	-	X	G
Butyl Alcohol (Butanol)	G	G	G	G	G	G	-	-	-
Butyraldehyde	-	-	F	-	-	-	-	-	-
Butyric Acid	-	-	F	-	-	-	-	-	-

F - Fair Resistance

G - Good Resistance

P - Poor Resistance (unsuitable)

X - Limited Resistance, dependent on service conditions



	Natural	Buna S	Neoprene	Buna N	Butyl	Hypalon	Silicon	Viton	Teflon
Calcium Acetate	G	-	P	G	-	-	-	-	-
Calcium Bisulfite	X	X	G	G	X	G	-	G	G
Calcium Chloride	G	G	G	G	G	G	G	G	G
Calcium Hydroxide	G	G	G	G	G	G	G	G	G
Calcium Hypochlorite	X	X	X	X	G	G	G	G	G
Calcium Nitrate	G	-	G	G	-	-	-	-	-
Calcium Sulfide	G	G	P	G	-	-	-	-	-
Caliche Liquors	G	G	G	G	G	G	-	-	-
Cane Sugar Liquors	G	G	G	G	G	G	-	-	G
Carbon Bisulfide	P	P	P	P	P	X	-	G	G
Carbon Dioxide, Dry	G	G	G	G	G	G	-	-	G
Carbon Monoxide, Hot (150F)	X	X	X	X	X	F	-	-	-
Carbon Tetrachloride	P	P	P	P	P	P	P	G	G
Castor Oil	G	G	G	G	G	G	-	-	-
Chinawood Oil	P	P	F	G	-	F	-	-	-
Chlorinated Solvents	P	P	P	X	P	P	P	-	-
Chlorine, Dry	G	F	P	F	F	P	-	G	G
Chlorine, Wet	F	F	P	F	F	P	-	G	G
Chloro Acetic Acid	-	P	P	P	-	G	-	-	-
Chloroform	P	P	P	P	P	-	-	G	G
Chlorosulphonic Acid	P	P	P	P	P	-	-	X	G
Chromic Acid	P	P	P	P	X	G	-	-	G
Citric Acid	G	F	G	F	F	G	-	G	G
Coconut Oil	P	P	P	-	-	-	-	-	-
Cod Liver Oil	P	P	P	-	-	-	-	-	-
Coke Oven Gas	X	X	X	X	X	G	-	-	G
Copper Chloride (150F)	F	F	F	G	G	-	G	G	G
Copper Sulfate (150F)	F	F	F	G	F	-	G	G	G
Corn Oil	P	P	F	G	G	F	-	-	-
Cotton Seed Oil	P	P	P	G	F	F	-	G	-
Creosote	P	P	F	G	P	F	-	G	G
Cresols	P	P	P	F	P	F	-	-	-
Cyclo Hexanone	P	P	P	P	F	-	-	-	-
Dibutylacetate	-	-	P	-	-	-	-	-	-
Dibutyl Amine	-	-	F	-	-	-	-	-	-
Dibutyl Ether	-	-	F	-	-	-	-	-	-
Dibutyl Phthalate	F	F	P	P	-	-	-	-	-
Dichlor Benzene	P	P	P	X	P	-	P	-	-
DiMethyl Anilia	P	P	P	P	X	-	-	-	-
DiPhenyl	P	P	P	P	P	-	X	-	-
Dow Therm A and E	P	P	P	P	P	F	-	G	G
Ethanol Amine	G	G	F	G	G	-	-	-	-
Ethyl Alcohol	G	G	G	G	G	-	-	G	G
Ethyl Acetate	F	F	P	P	F	P	-	X	G
Ethyl Benzoate	P	P	P	X	P	-	-	-	-
Ethyl Cellulose	F	F	F	F	F	-	-	-	-
Ethyl Chloride	G	G	G	G	G	F	P	-	G
Ethyl Ether	X	X	X	F	X	F	P	-	-
Ethyl Formate	-	-	X	-	-	-	-	-	-
Ethylene DiChloride	P	P	P	P	P	-	-	-	-
Ethylene Glycol	G	G	G	G	G	G	-	G	G
Ethylene Trichloride	-	-	P	P	-	-	-	-	-
Ferric Chloride (150F)	G	G	G	G	G	G	-	G	G
Ferric Sulfate (150F)	G	G	G	G	G	G	-	-	-
Formaldehyde	G	G	G	F	G	G	-	X	G
Formic Acid	G	G	F	P	G	G	-	-	-
Freon	P	P	F	F	F	-	-	F	G



	Natural	Buna S	Neoprene	Buna N	Butyl	Hypalon	Silicon	Viton	Teflon
Gasoline	P	P	G	G	P	P	P	G	G
Gelatin	G	G	G	G	G	G	-	G	G
Glucose	G	G	G	G	G	G	-	G	G
Glue	F	F	G	G	F	G	-	G	G
Glycerin	G	G	G	G	G	G	-	-	-
Green Sulfate Liquor	G	G	G	G	G	G	-	-	-
Hexane	P	P	G	G	-	-	F	-	-
Hexyl Alcohol	-	-	G	-	-	-	-	-	-
Hydrobromic Acid	G	P	P	F	G	G	F	-	G
Hydrochloric Acid, Cold	G	F	F	F	G	-	G	G	G
Hydrochloric Acid, Hot	F	P	P	P	X	-	F	G	G
Hydrocyanic Acid	F	F	F	F	-	G	-	-	G
Hydrofluoric Acid, Cold	P	P	P	F	X	-	P	G	-
Hydrofluoric Acid, Hot	X	X	X	P	X	-	P	G	-
Hydrofluosilicic Acid	G	G	F	G	G	-	P	-	-
Hydrogen Gas	F	F	G	G	G	-	G	-	G
Hydrogen Peroxide	F	F	P	G	F	X	G	G	G
Hydrogen Sulfide	X	X	F	X	G	-	-	G	G
Isophorone	-	-	-	P	-	-	-	-	-
Iso Propyl Ether	P	P	F	G	P	-	-	-	G
Kerosene	P	P	F	G	P	F	P	G	G
Lacquers	P	P	P	P	P	P	-	X	G
Lacquer Solvents	P	P	P	P	P	P	-	X	G
Lactic Acid	X	X	X	X	X	P	-	G	G
Lard	P	X	F	G	F	-	F	-	-
Linoleic Acid	P	P	F	F	-	-	-	-	G
Linseed Oil	X	X	F	G	X	G	P	-	-
Lubricating Oils	P	P	G	C	P	-	G	-	-
Lubricating Oils, Refined	F	F	G	G	P	F	G	G	-
Magnesium Chloride (150F)	G	G	F	G	G	G	-	G	G
Magnesium Hydroxide (150F)	G	G	F	G	G	G	G	G	G
Magnesium Sulfate (150F)	G	G	G	G	G	G	G	G	G
Mercuric Chloride	G	G	F	G	G	G	-	-	G
Mercury	G	G	G	G	G	G	-	G	G
Mesityl Oxide	P	P	P	P	X	-	-	-	-
Methyl Acetate	F	F	P	P	-	-	-	X	G
Methyl Alcohol, Methanol	G	G	G	G	G	G	-	F	G
Methyl Bromides	-	-	P	-	-	-	-	-	-
Methyl Butyl Ketone	P	P	F	P	X	-	-	-	-
Methyl Ethyl Ketone	P	P	F	P	F	-	-	X	G
Methyl Formate	X	X	G	P	F	-	-	-	G
Methyl Oleate	-	-	P	-	-	-	-	-	-
Methyl Salicylate	-	-	P	P	-	-	-	-	-
Methylene Chloride	X	X	F	X	-	P	-	G	G
Milk	G	G	G	G	G	G	-	G	G
Mineral Oils	X	X	F	G	P	F	G	G	-
Monochlor	-	-	P	-	-	-	-	-	-
Monobrom Benzol	P	P	P	P	P	-	-	-	-
Mono Methyl Aniline	-	-	P	-	-	-	-	-	-

F - Fair Resistance

P - Poor Resistance (unsuitable)

G - Good Resistance

X - Limited Resistance, dependent on service conditions



	Natural	Buna S	Neoprene	Buna N	Butyl	Hypalon	Silicon	Viton	Teflon
Naphtha (Petroleum Ether)	P	P	F	F	P	-	P	G	G
Naphthalene	P	P	P	P	P	-	-	G	G
Natural Gas	F	F	G	G	P	G	-	G	G
Nickel Chloride (150F)	G	G	G	G	G	G	-	G	G
Nickel Sulfate (150F)	G	G	G	G	G	G	-	G	G
Nitric Acid	P	P	P	P	X	X	G	F	G
Nitric Acid, Diluted	P	P	P	P	G	G	G	F	G
Nitrobenzene	P	P	P	P	P	G	-	G	G
Nitroethane	G	F	F	P	G	-	-	-	-
Nitropropane	X	X	X	P	G	-	-	-	-
Octyl Alcohol	-	-	G	-	-	-	-	-	-
Oleic Acid	F	F	F	G	G	F	P	-	-
Oleum Spirits	P	P	F	F	-	-	P	-	G
Olive Oil	P	P	F	-	-	-	-	-	-
Oxalic Acid	F	F	F	F	G	G	-	-	G
Oxygen,Cold	X	X	G	X	G	-	G	G	G
Oxygen,Under 500F	X	X	X	X	-	-	-	G	G
Palmitic Acid	F	F	X	G	P	F	-	G	G
Perchloric Acid	-	-	X	-	-	-	-	-	-
Petroleum Oils, Cold	X	X	G	G	P	-	F	-	-
Petroleum Oils,Crude Under 500f	X	X	G	G	P	G	-	G	-
Petroleum Oils, Hot	P	P	P	P	P	-	-	-	-
Phenol	P	P	P	P	X	-	-	G	G
Phosphoric Acid	X	X	X	P	X	-	X	-	G
Phosphoric Acid, Crude	X	X	X	X	X	G	-	G	G
Picric Acid, Molten	X	X	X	X	X	-	P	-	G
Picric Acid, Solution	G	X	G	G	G	G	-	-	G
Pine Oil	P	P	P	F	P	-	-	-	-
Potassium Chloride	G	G	F	G	G	G	-	G	G
Potassium Cyanide	G	G	F	G	G	G	-	G	G
Potassium Hydroxide	G	G	F	G	G	G	-	G	G
Potassium Sulfate	G	G	F	G	G	G	-	G	G
Producer Gas	P	P	F	G	P	-	G	-	-
Propane	P	P	F	G	P	F	G	-	G
Propyl Acetate	-	-	F	-	-	-	-	-	-
Propyl Alcohol	G	G	G	G	G	-	-	G	G
Pyridine	P	P	P	P	G	-	-	-	-
Rosin Oil	-	-	G	-	-	-	-	-	-
Sewage	X	X	F	G	P	G	G	-	-
Soap Solution	X	X	F	G	G	G	G	-	G
Sodium Bicarbonate	G	G	G	G	G	-	-	-	-
Sodium Bisulfate	G	G	G	G	G	-	-	G	G
Sodium Carbonate	G	G	G	G	G	-	G	G	G
Sodium Chloride	G	G	G	G	G	G	G	G	G
Sodium Cyanide	G	G	G	G	G	G	-	G	G
Sodium Hydroxide	X	X	X	X	G	X	G	G	G
Sodium Hypochlorittw	X	X	P	X	G	G	G	F	G

F - Fair Resistance

P - Poor Resistance (unsuitable)

G - Good Resistance

X - Limited Resistance, dependent on service conditions



	Natural	Buna S	Neoprene	Buna N	Butyl	Hypalon	Silicon	Viton	Teflon
Sodium Metaphosphate	G	G	X	G	G	-	-	-	G
Sodium Nitrate	X	X	X	X	G	-	-	G	G
Sodium Perborate	X	X	X	X	G	-	-	-	G
Sodium Peroxide	X	X	X	X	G	G	-	G	G
Sodium Phosphates	G	G	X	G	G	-	-	-	G
Sodium Silicate	G	G	G	G	G	-	G	-	G
Sodium Sulfate	G	G	G	G	G	G	G	G	G
Sodium Sulfide	G	G	G	G	G	-	-	G	G
Sodium Thiosulfate	G	G	G	G	G	-	G	G	G
Soya Bean Oil	X	X	F	G	-	G	-	-	-
Stannic Chloride	G	G	G	G	F	G	-	-	-
Steam Under 500 F	X	G	X	G	-	-	G	G	-
Stearic Acid	X	X	F	G	X	G	G	-	-
Sulfur	F	F	G	F	F	G	-	G	G
Sulfur Chloride	P	P	F	F	P	G	-	-	-
Sulfur Dioxide, Dry	X	X	X	X	X	G	-	-	G
Sulfur Trioxide	G	X	P	X	X	F	-	-	G
Sulfuric Acid, 10%	G	G	G	G	G	G	G	G	G
Sulfuric Acid, Conc.	P	P	P	P	X	G	P	G	G
Sulfuric Acid, Fuming	P	P	P	P	P	P	P	-	-
Sulfurous Acid	G	X	X	X	X	-	-	-	G
Tannic Acid	G	X	X	X	X	G	F	-	G
Tanning Liquor	-	-	P	G	-	-	-	-	-
Tar	X	X	X	X	P	G	F	-	G
Tartaric Acid	G	X	X	X	X	G	G	-	G
Toluene	P	P	P	X	P	P	P	G	G
Trichlorethylene	P	P	P	P	P	P	P	G	G
Tricresyl Phosphate	G	F	F	P	G	-	-	-	-
Tri Ethanol Amine	G	G	G	G	G	-	-	-	-
Tri Butyl Phosphate	F	X	P	P	F	-	-	-	-
Tri Phenyl Phosphate	-	-	-	P	-	-	-	-	-
Turpentine	P	P	P	F	P	G	X	-	-
Vegetable Oils	X	X	F	G	G	-	X	-	-
Vinegar	X	X	X	X	G	G	G	-	G
Water	G	G	P	G	G	G	G	G	G
Whiskey & Wines	X	X	X	X	G	G	G	-	G
Xylene	P	P	P	P	P	-	P	G	G
Xyliidine	P	P	P	P	P	-	-	-	-
Zinc Chloride	X	X	X	X	G	G	-	-	G
Zinc Sulfate	G	G	G	G	G	G	-	-	G

F - Fair Resistance

P - Poor Resistance (unsuitable)

G - Good Resistance

X - Limited Resistance, dependent on service conditions



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Acatic Acid	10% aq Sol.	Satisfactory
	60% aq Sol.	Satisfactory
Aluminum Chloride		Satisfactory
Aluminum Fluoride		Satisfactory
Aluminum Hydroxide		Satisfactory
Aluminum Nitrate		Satisfactory
Aluminum Oxalate		Satisfactory
Aluminum Oxychloride		Satisfactory
Aluminum Sulphate		Satisfactory
Ammonium Bicarbonate		Satisfactory
Ammonium Bifluoride		Satisfactory
Ammonium Chloride		Satisfactory
Ammonium Fluoride		Satisfactory
Ammonium Hydrosulphide		Satisfactory
Ammonium Hydroxide		Satisfactory
Ammonium Metaphosphate		Satisfactory
Ammonium Nitrate		Satisfactory
Ammonium Oxalate		Satisfactory
Ammonium Persulphate		Satisfactory
Ammonium Phosphate		Satisfactory
Ammonium Sulphate		Satisfactory
Ammonium Sulphide		Satisfactory
Ammonium Thiocyanate		Satisfactory
Amyl Alcohol		Satisfactory
Aniline Sulphate		Satisfactory
Antimony Chloride		Satisfactory
Barium Carbonate		Satisfactory
Barium Chloride		Satisfactory
Barium Hydroxide		Satisfactory
Barium Sulphate		Satisfactory
Barium Sulphide		Satisfactory
Bismuth Carbonate		Satisfactory
Borax		Satisfactory
Boric Acid		Satisfactory
Butyl Alcohol		Satisfactory
Butyric Acid	20% aq Sol.	Satisfactory
Calcium Carbonate		Satisfactory
Calcium Chlorate		Satisfactory
Calcium Chloride	aq Sol	Satisfactory
Calcium Hydroxide		Satisfactory
Calcium Hypochlorite		Satisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Calcium Nitrate		Satisfactory
Calcium Phosphate		Satisfactory
Calcium Sulphate		Satisfactory
Carbonic Acid		Satisfactory
Castor Oil		Satisfactory
Cetyl Alcohol		Satisfactory
Chrome Alum		Satisfactory
Citric Acid		Satisfactory
Copper Chloride		Satisfactory
Copper Cyanide		Satisfactory
Copper Fluoride		Satisfactory
Copper Nitrate		Satisfactory
Copper Sulphate		Satisfactory
Cupric Chloride		Satisfactory
Cupric Fluoride		Satisfactory
Cupric Nitrate		Satisfactory
Cupric Suphate		Satisfactory
Detergents, Synthetic	All Conc.	Satisfactory
Diethylene Glycol		Satisfactory
Dimethylcarbinol		Satisfactory
Disodium Phoshate		Satisfactory
Ethyl Alcohol	40% w/w in water 100%	Satisfactory Satisfactory
Ethylene Glycol		Satisfactory
Ferric Chloride		Satisfactory
Ferric Nitrate		Satisfactory
Ferric Sulphate		Satisfactory
Ferrous Ammonium Citrate		Satisfactory
Ferrous Chloride		Satisfactory
Ferrous Sulphate		Satisfactory
Formaldahyde	40% w/w in water	Satisfactory
Gallic Acid		Satisfactory
Glycerine		Satisfactory
Hexyl Alcohol		Satisfactory
Hydrobromic Acid	50% aq Sol. 100%	Satisfactory Satisfactory
Hydrochoric Acid	10% aq Sol. 22% aq Sol. Conc.	Satisfactory Satisfactory Satisfactory
Hydrofluoric Acid	4% aq Sol. 40% aq Sol.	Satisfactory Satisfactory
Hydrogene Bromide	Anhydrous	Satisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Hydrogen Chloride	Anhydrous	Satisfactory
Hydrogen Fluoride	Anhydrous	Satisfactory
Hydrogen Peroxide	3% (10 Vol.)	Satisfactory
	12% (40 Vol.)	Satisfactory
	30% (100 Vol.)	Satisfactory
	90% and above	Satisfactory
Hydrogen Phosphide		Satisfactory
Hydrogen Sulphite		Satisfactory
Hydroquinone		Satisfactory
Isopropyl Alcohol		Satisfactory
Lactic Acid	10% aq Sol.	Satisfactory
Lead Acetate		Satisfactory
Lead Arsenate		Satisfactory
Lead Nitrate		Satisfactory
Lead Tetraethyl		Satisfactory
Magnesium Carbonate		Satisfactory
Magnesium Chloride		Satisfactory
Magnesium Hydroxide		Satisfactory
Magnesium Nitrate		Satisfactory
Magnesium Sulphate		Satisfactory
Malic Acid		Satisfactory
Manganese Suphate		Satisfactory
Mercuric Cyanide		Satisfactory
Marcurous Nitrate		Satisfactory
Metallic Soaps (water soluble)		Satisfactory
Methyl Alcohol	6% aq Sol.	Satisfactory
Mineral Oils		Satisfactory
Nickel Chloride		Satisfactory
Nickel Nitrate		Satisfactory
Nickel Sulphate		Satisfactory
Nitric Acid	5% aq Sol.	Satisfactory
	10% aq Sol.	Satisfactory
	25% aq Sol.	Satisfactory
	50% aq Sol.	Satisfactory
Octyl Alcohol		Satisfactory
Oleic Acid		Satisfactory
Oxalic Acid		Satisfactory
Pslmitic Acid		Satisfactory
Phosphates		Satisfactory
Phosphoric Acid	20% aq Sol.	Satisfactory
	30% aq Sol.	Satisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Phosphorus Pentoxide		Satisfactory
Photographic Developers		Satisfactory
Photographic Emulsions		Satisfactory
Photographic Fixing Sol		Satisfactory
Phthalic Anhydride		Satisfactory
Picric Acid	1% w/w in water 10% w/w in alcohol	Satisfactory Satisfactory
Potassium Bicarbonate		Satisfactory
Potassium Bichromate		Satisfactory
Potassium Bisulphite		Satisfactory
Potassium Borate		Satisfactory
Potassium Bromate		Satisfactory
Potassium Bromide		Satisfactory
Potassium Carbonite		Satisfactory
Potassium Chloride		Satisfactory
Potassium Chromate		Satisfactory
Potassium Cuprocyanide		Satisfactory
Potassium Cyanide		Satisfactory
Potassium Dichromate		Satisfactory
Potassium Ferrocyanide		Satisfactory
Potassium Fluoride		Satisfactory
Potassium Hydroxide	1% aq Sol. 10% aq Sol. Conc.	Satisfactory Satisfactory Satisfactory
Potassium Hypochlorite		Satisfactory
Potassium Nitrate		Satisfactory
Potassium Perborate		Satisfactory
Potassium Perchlorite		Satisfactory
Potassium Permanganate		Satisfactory
Potassium Persulphate		Satisfactory
Potassium Phosphate		Satisfactory
Potassium Sulphate		Satisfactory
Potassium Sulphide		Satisfactory
Potassium Thiosulphate		Satisfactory
Propargyl Alcohol		Satisfactory
Propargyl Glycol		Satisfactory
Silver Acetate		Satisfactory
Silver Cyanide		Satisfactory
Sodium Acetate		Satisfactory
Sodium Acid Sulphate		Satisfactory
Sodium Bezoate		Satisfactory
Sodium Bicarbonate		Satisfactory
Sodium Bisulfate		Satisfactory
Sodium Borate		Satisfactory
Sodium Bromide		Satisfactory
Sodium Carbonate		Satisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Sodium Chlorate		Satisfactory
Sodium Chlorids		Satisfactory
Sodium Cyanide		Satisfactory
Sodium Fluoride		Satisfactory
Sodium Hydroxide	1% aq Sol. 10% aq Sol. 40% aq Sol. Conc. 15% C1	Satisfactory Satisfactory Satisfactory Satisfactory Satisfactory
Sodium Hypochlorite		Satisfactory
Sodium Hyposulphate		Satisfactory
Sodium Nitrate		Satisfactory
Sodium Nitrite		Satisfactory
Sodium Perborate		Satisfactory
Sodium Peroxide		Satisfactory
Sodium Phosphate		Satisfactory
Sodium Silicate		Satisfactory
Sodium Sulphate		Satisfactory
Sodium Sulphide	25% aq Sol. Conc.	Satisfactory Satisfactory
Sodium Tetraborate		Satisfactory
Sodium Thiosulphate		Satisfactory
Stannic Chlorids		Satisfactory
Stannous Chloride		Satisfactory
Stearic Acid		Satisfactory
Sulphur Dioxide	Dry	Satisfactory
Sulphuric Acid	10% aq Sol. 20% aq Sol. 30% aq Sol. 40% aq Sol. 45% aq Sol. 50% aq Sol.	Satisfactory Satisfactory Satisfactory Satisfactory Satisfactory Satisfactory
Sulphurous Acid	10% aq Sol. 30% aq Sol.	Satisfactory Satisfactory
Tannic Acid		Satisfactory
Tartaric Acid		Satisfactory
Tetra Ethyl Lead		Satisfactory
Triethanolamina		Satisfactory
Tristhylene Glycol		Satisfactory
Trisodium Phosphate		Satisfactory
Urea		Satisfactory
Vinegar		Satisfactory
Water		Satisfactory
Zinc Chloride		Satisfactory
Zinc Sulphide		Satisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Acetaldehyde	40% aqueous	Unsatisfactory
	100%	Unsatisfactory
Acetic Acid	Glacial	Unsatisfactory
Acetic Anhydrides		Unsatisfactory
Acetona		Unsatisfactory
Acetonitrile		Unsatisfactory
Acetophenone		Unsatisfactory
Allyl Alcohol		Unsatisfactory
Allyl Chloride		Unsatisfactory
Ammonia	Liquid	Unsatisfactory
Ammonium Sulphide		Unsatisfactory
Amyl Acetate		Unsatisfactory
Amyl Chloride		Unsatisfactory
Aniline		Unsatisfactory
Aniline Hydrochloride		Unsatisfactory
Benzaldehyde		Unsatisfactory
Benzene		Unsatisfactory
Benzoic Acid		Unsatisfactory
Benzoyl Chloride		Unsatisfactory
Benzyl Acetate		Unsatisfactory
Benzyl Alcohol		Unsatisfactory
Bromine		Unsatisfactory
Butanediol		Unsatisfactory
Butyl Acetate		Unsatisfactory
Butyl Chloride		Unsatisfactory
Butyraldehyde		Unsatisfactory
Butyric Acid	Conc.	Unsatisfactory
Calcium Chloride	20% in Methyl Alcohol	Unsatisfactory
Carbon Disulphide		Unsatisfactory
Carbon Tetrachloride		Unsatisfactory
Choracetic Acid		Unsatisfactory
Chloral Hydrate		Unsatisfactory
Chlorine Trifluoride		Unsatisfactory
Chlorine Water	Sat. Sol.	Unsatisfactory
Chlorobenzene		Unsatisfactory
Chlorophorm		Unsatisfactory
Chlorosulphonic Acid		Unsatisfactory
Chromic Acid	Plasting Sol.	Unsatisfactory
Creosote		Unsatisfactory
Cresols		Unsatisfactory
Cresylic Acids		Unsatisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Crotonaldehyde		Unsatisfactory
Cyclohexanol		Unsatisfactory
Cyclohexanona		Unsatisfactory
Diamyl Ether		Unsatisfactory
Dioxytl Phthalate		Unsatisfactory
Dichloreathylene		Unsatisfactory
Dichlorobenzene		Unsatisfactory
Diethyl Keytone		Unsatisfactory
Dieoctyl Ththalate		Unsatisfactory
Dioxane		Unsatisfactory
Ether		Unsatisfactory
Ethyl Acetate		Unsatisfactory
Ethyl Acrylate		Unsatisfactory
Ethyl Butyrate		Unsatisfactory
Ethyl Chloride		Unsatisfactory
Ethyl Ether		Unsatisfactory
Ethyl Formate		Unsatisfactory
Ethyl Lactate		Unsatisfactory
Ethylene Bromide		Unsatisfactory
Ethylene Chloride		Unsatisfactory
Ethylene Dibromide		Unsatisfactory
Ethylene Dichloride		Unsatisfactory
Ethylene Oxide		Unsatisfactory
Flourine		Unsatisfactory
Formic Acid	50% aq sol 100%	Unsatisfactory Unsatisfactory
Furfural		Unsatisfactory
Furfuryl Alcohol		Unsatisfactory
Glacial Acetic Acid		Unsatisfactory
Glycerol Menobenzyl Ether		Unsatisfactory
Hydrofluoric Acid	60% aq Sol. Conc.	Unsatisfactory Unsatisfactory
Hypochlorous Acid		Unsatisfactory
Iodine	Sol in Potassium Iodide	Unsatisfactory
Iaophorone		Unsatisfactory
Lactic Acid	100%	Unsatisfactory
Malaic Acid	Conc.	Unsatisfactory
Marcuic Chloride		Unsatisfactory
Maityl Oxide		Unsatisfactory
Methyl Aectate		Unsatisfactory
Methyl Bromide		Unsatisfactory
Methyl Chloride		Unsatisfactory



THOR Tarp
Div of **ODIN** International, Inc.
888-ODIN-INC



Chemical	Concentration	Degree of Attack
Methyl Cylohexanone		Unsatisfactory
Methyl Ethyl Ketone		Unsatisfactory
Methyl Isobutyl Ketone		Unsatisfactory
Methyl Methacrylate		Unsatisfactory
Methyl Sulphate		Unsatisfactory
Methylene Chloride		Unsatisfactory
Mineral Oils		Unsatisfactory
Mixed Acids (Sulphuric/Nitric	Various Proportions	Unsatisfactory
Monochlorbenzene		Unsatisfactory
Naphthalene		Unsatisfactory
Nitric Acid	70% ap Sol. 95% aq Sol.	Unsatisfactory Unsatisfactory
Nitrobenzene		Unsatisfactory
Nitropropane		Unsatisfactory
Nitrous Fumes		Unsatisfactory
Perchloric Acid		Unsatisfactory
Petroleum Ether		Unsatisfactory
Phenol		Unsatisfactory
Pheynlcarbinol		Unsatisfactory
Phenylhydrazine		Unsatisfactory
Phenylhydrazine Hydrochloride		Unsatisfactory
Phosphorus Trichloride		Unsatisfactory
Polyglycol Ethers		Unsatisfactory
Potassium Hydroxide	Conc.	Unsatisfactory
Propylene Dichloride		Unsatisfactory
Propylene Oxide		Unsatisfactory
Sodium Bezoate		Unsatisfactory
Sodium Hydroxide	40% aq Sol. Conc.	Unsatisfactory Unsatisfactory
Sulphur Dioxide	Moist Liquid	Unsatisfactory Unsatisfactory
Sulphuric Acid	98% aq Sol. Fuming	Unsatisfactory Unsatisfactory
Tetrahydrofuran		Unsatisfactory
Tetrahydronaphthalene		Unsatisfactory
Tetralin		Unsatisfactory
Toluene		Unsatisfactory
Tributyl Phosphate		Unsatisfactory
Trichloricaetic Acid		Unsatisfactory
Trichloroethane		Unsatisfactory
Trichoroethylene		Unsatisfactory
Trichlorobenzene		Unsatisfactory
Tricrssyl Phosphate		Unsatisfactory
Vinyl Acetate		Unsatisfactory