



# THOR Tarp

DIV. OF **ODIN** INTERNATIONAL, INC



## DuraShield 6000 ASFR

ANTI-STATIC FLAME RESISTANT FABRIC  
PHYSICAL CHARACTERISTICS

CONSTRUCTION	HDPE 900 DENIER ( $\pm 10\%$ ) 8x8 counts per inch warp and fill
COATING	2 MILS EACH SIDE ( $\pm 10\%$ )
FLAME RETARDANT	MEETS CPA-84 FLAME RESISTANT MATERIAL
SURFACE RESISTANCE	7.83 x 10 <sup>10</sup> ohms (ASTM D-257)
STATIC DECAY	$\geq 2$ SECONDS (FTMS 101C, Method 4046)
COLORS	FROSTY CLEAR
WIDTH	60"
WEIGHT	3.5oz. PER SQUARE YARD ( $\pm 10\%$ ) (ASTM D-1910)
TENSILE STRENGTH	128 lbs. warp 130 lbs. fill (ASTM D-1682, grab)
TEAR STRENGTH	31 lbs. warp 28 lbs. fill (ASTM D-1682 Tongue)
BURSTING STRENGTH	130.0 P.S.I. (ASTM D-751 Mullen)
HYDROSTATIC RESISTANCE	65 P.S.I. (ASTM D-751)
TOTAL THICKNESS	6.5 mils ( $\pm 10\%$ )

THESE ARE TYPICAL PROPERTY VALUES AND ARE INTENDED AS GUIDES ONLY, AND DO NOT RELIEVE THE USER FROM ITS RESPONSIBILITY TO INVESTIGATE AND UNDERSTAND TEST DATE AND SOURCES OF INFORMATION AND TO COMPLY WITH ALL PROCEDURES FOR SAFE HANDLING AND USE OF THIS MATERIAL.

CORPORATE HQ: P.O. Box 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511  
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM