



THOR Tarp

Div. OF

ODIN

INTERNATIONAL, INC



WeldShield 2190 AF-B

GENERAL DESCRIPTION & APPLICATIONS

WeldShield 2190 AF-B is coated with a proprietary coating. The base fabric is manufactured using highly texturized silica yarn. Abrasion resistant coating for tough welding applications. Will shed molten splatter and sparks to 3000°F if used on a 15° incline or greater. Recommended for curtains, blankets and screens.

PHYSICAL PROPERTIES

Weight	23 oz/Square Yard
Construction (warp x fill)	20 x 14
Weave	Plain
Thickness	0.040"
Breaking Strength (minimum)	Warp – 350 lbs. Fill – 290 lbs.
Abrasion Resistance, Taber	700 + cycles to failure using CS 10 wheel with 1000 Grams weight resistance at 50% vacuum level.
*Temperature	Continuous temperatures to 1100°F (593° C) and higher short duration temperatures.
* K Factor (Heat Conductivity)	0.3399 BTU/inch/hr/sq ft/°F

ORDERING INFORMATION

Length of Roll: 50 yards

*for basic fabric

To the best of our knowledge, the information contained herein is accurate. The information provided is based upon data furnished by our suppliers. However, ODIN International, Inc. assumes no liability whatsoever for the accuracy or completeness of the information contained herein. While believed to be reliable, the information of products are intended for use by skilled persons at their own risk. Final determination of suitability of any material is the sole responsibility of the user. All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards that exist.

CORPORATE HQ: P.O. Box 811 • OCONOMOWOC, WI 53066-0811 • 262-569-7171 • FAX: 262-569-1511
TOLL FREE: 1-888-ODIN-INC • 1-888-634-6462 • EMAIL: INFO@THORTARP.COM

WWW.THORTARP.COM