

DuraShield 3000 FR *Fire Retardant Woven, Coated Polyethylene*

DESCRIPTION	Premium flame retardant coated fabrics for industrial and construction applications.				
COUNT	Nominal 5 x 4 tapes/inch				
WEIGH	3.0 oz per square yard (100 gsm) \pm 10%				
TENSILE STRENGTH (Grab Method)	Warp	-	75	lbs	ASTM D751 (Meth. A)
	Weft	-	65	lbs	
TEAR STRENGTH (Trapezoidal Method)	Warp	-	32	lbs	ASTM D4533
(Weft	-	32	lbs	
MULLEN BURST	130 psi				ASTM D751

The above physical test results are representative data collected from a number of production runs. Results for an individual roll (based on at least three specimens) may vary from the average by \pm 10%.

COATING THICKNESS	1.3 mil average, two sides
	30 gsm average, two sides

SCRIM TYPE

Clear tapes

Conforms to NFPA 701, CPAI-84 sections 6 & 7, Boston Fire Marshall's Test, and California Fire Code

Corporate HQ: P.O. Box 811 • Oconomowoc, WI 53066-0811 • 262-569-7171 • Fax: 262-569-1511 Toll Free: 1-888-0DIN-INC • 1-888-634-6462 • Email: INFO@THORTARP.COM